



Test Report issued under the responsibility of:



TEST REPORT IEC 62133 Secondary Cells and Batteries Containing Alkaline or Other Non-Acid Electrolytes – Safety Requirements for Portable Sealed Secondary Cells, and for Batteries Made from Them, for Use in Portable Applications	
Report Number..... :	60363389 001
Date of issue..... :	2020-05-08
Total number of pages	24 pages
Name of Testing Laboratory preparing the Report	TÜV Rheinland (Shenzhen) Co., Ltd.
Applicant's name	Master Battery, S.L.
Address..... :	2, Dehesa Vieja Street, La Dehesa Industrial Park, 28052, Madrid, Spain
Test specification:	
Standard	IEC 62133:2012
Test procedure	CB Scheme
Non-standard test method	N/A
Test Report Form No. :	IEC62133C
Test Report Form(s) Originator :	UL (Demko)
Master TRF	2018-07-27
Copyright © 2018 IEC System of Conformity Assessment Schemes for Electrotechnical Equipment and Components (IECEE System). All rights reserved.	
This publication may be reproduced in whole or in part for non-commercial purposes as long as the IECEE is acknowledged as copyright owner and source of the material. IECEE takes no responsibility for and will not assume liability for damages resulting from the reader's interpretation of the reproduced material due to its placement and context.	
If this Test Report Form is used by non-IECEE members, the IECEE/IEC logo and the reference to the CB Scheme procedure shall be removed.	
This report is not valid as a CB Test Report unless signed by an approved CB Testing Laboratory and appended to a CB Test Certificate issued by an NCB in accordance with IECEE 02.	
General disclaimer:	
The test results presented in this report relate only to the object tested. This report shall not be reproduced, except in full, without the written approval of the Issuing CB Testing Laboratory. The authenticity of this Test Report and its contents can be verified by contacting the NCB, responsible for this Test Report.	

Test item description :	Rechargeable LiFePO4 Cell	
Trade Mark :	N/A	
Manufacturer	Same as applicant	
Model/Type reference	32700 6000mAh	
Ratings	3.2V, 6000mAh, 19.2Wh	
Responsible Testing Laboratory (as applicable), testing procedure and testing location(s):		
<input checked="" type="checkbox"/>	CB Testing Laboratory:	TÜV Rheinland (Shenzhen) Co., Ltd.
Testing location/ address :	1F East & 2-4F, Cybio Technology Building No. 1, No. 16 Kejibei 2nd Road, High-Tech Industrial Park North, Nanshan District, 518057, Shenzhen, China	
Tested by (name, function, signature) :	Harris Yin (Engineer)	
Approved by (name, function, signature) ... :	Jason Tang (Reviewer)	
<input type="checkbox"/>	Testing procedure: CTF Stage 1:	
Testing location/ address :		
Tested by (name, function, signature) :		
Approved by (name, function, signature) ... :		
<input type="checkbox"/>	Testing procedure: CTF Stage 2:	
Testing location/ address :		
Tested by (name + signature)		
Witnessed by (name, function, signature) . :		
Approved by (name, function, signature) ... :		
<input type="checkbox"/>	Testing procedure: CTF Stage 3:	
<input type="checkbox"/>	Testing procedure: CTF Stage 4:	
Testing location/ address :		
Tested by (name, function, signature) :		
Witnessed by (name, function, signature) . :		
Approved by (name, function, signature) ... :		
Supervised by (name, function, signature) :		

<p>List of Attachments (including a total number of pages in each attachment): Attachment 1: Photo documentation (1 page)</p>	
<p>Summary of testing:</p>	
<p>Tests performed (name of test and test clause): cl.5.6.2 Design recommendation(Lithium system); cl.8.1 Charging procedure for test purposes (for Cells); cl.8.2.1 Continuous charging at constant voltage (Cells); cl.8.3.1 External short circuit (Cells); cl.8.3.3 Free fall (Cells); cl.8.3.4 Thermal abuse (Cells); cl.8.3.5 Crush (Cells); cl.8.3.7 Forced discharge (Cells); cl.8.3.9 Design evaluation - Forced internal short circuit (Cells)</p> <p>Tests are made with the number of cells specified in IEC 62133: 2012 (Second Edition) Table 2.</p>	<p>Testing location: TÜV Rheinland (Shenzhen) Co., Ltd. 1F East & 2-4F, Cybio Technology Building No. 1, No. 16 Kejibei 2nd Road, High-Tech Industrial Park North, Nanshan District, 518057, Shenzhen, China</p>
<p>Summary of compliance with National Differences (List of countries addressed):</p> <p>N/A</p> <p><input checked="" type="checkbox"/> The product fulfils the requirements of <u>EN 62133: 2013</u></p>	

Copy of marking plate:

The artwork below may be only a draft. The use of certification marks on a product must be authorized by the respective NCBs that own these marks.

Rechargeable LiFePO4 Cell				
+	32700	6000mAh	3.2V 19.2Wh	-
	6000mAh	IFpR33/71	2020/04/08	
Master Battery, S.L.				

Remark: 2020/04/08 represents the manufacture date.

Test item particulars.....:	
Recommend charging method declared by the manufacturer	Charging the cell with 3000mA constant current until 3.65V, then constant voltage until charge current reduces to 60mA at ambient 20°C±5°C
Discharge current (0,2 I_t A)	1200mA
Specified final voltage	2.0V
Chemistry	<input type="checkbox"/> nickel systems <input checked="" type="checkbox"/> lithium systems
Recommend of charging limit for lithium system	
Upper limit charging voltage per cell.....	3.65V
Maximum charging current	18000mA
Charging temperature upper limit	60°C
Charging temperature lower limit.....	0°C
Polymer cell electrolyte type	<input type="checkbox"/> gel polymer <input type="checkbox"/> solid polymer
Possible test case verdicts:	
- test case does not apply to the test object.....: N/A	
- test object does meet the requirement.....: P (Pass)	
- test object does not meet the requirement.....: F (Fail)	
Testing.....:	
Date of receipt of test item : 2020-04-13	
Date (s) of performance of tests : 2020-04-17 to 2020-04-29	
General remarks:	
"(See Enclosure #)" refers to additional information appended to the report. "(See appended table)" refers to a table appended to the report.	
Throughout this report a <input type="checkbox"/> comma / <input checked="" type="checkbox"/> point is used as the decimal separator.	
Manufacturer's Declaration per sub-clause 4.2.5 of IEC60080-02:	
The application for obtaining a CB Test Certificate includes more than one factory location and a declaration from the Manufacturer stating that the sample(s) submitted for evaluation is (are) representative of the products from each factory has been provided	<input type="checkbox"/> Yes <input checked="" type="checkbox"/> Not applicable
When differences exist; they shall be identified in the General product information section.	
Name and address of factory (ies) : Same as applicant	

General product information and other remarks:

The cell consists of the positive electrode plate, negative electrode plate, separator, electrolyte and case. The positive and negative electrode plates are housed in the case in the state being separated by the separator.


The main features of the cell are shown as below (clause 8.1.1):

Model	Nominal capacity	Nominal voltage	Nominal Charge Current	Nominal Discharge Current	Maximum Charge Current	Maximum Discharge Current	Maximum Charge Voltage	Cut-off Voltage
32700 6000mAh	6000mAh	3.2V	3000mA	3000mA	18000mA	18000mA	3.65V	2.0V

The main features of the cell are shown as below (clause 8.1.2):

Model	Upper limit charge voltage	Taper-off current	Lower charge temperature	Upper charge temperature
32700 6000mAh	3.65V	300mA	0°C	60°C

Construction:



D3	32.45mm max
H	70.9mm max

Cell

Circuit diagram:

Cell only.

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
4	Parameter measurement tolerances		P
	Parameter measurement tolerances		P
5	General safety considerations		P
5.1	General		P
5.2	Insulation and wiring		P
	The insulation resistance between the positive terminal and externally exposed metal surfaces of the battery (excluding electrical contact surfaces) is not less than 5 MΩ	No metal case exists.	N/A
	Insulation resistance (MΩ)		—
	Internal wiring and insulation are sufficient to withstand maximum anticipated current, voltage and temperature requirements		P
	Orientation of wiring maintains adequate creepage and clearance distances between conductors		P
	Mechanical integrity of internal connections accommodates reasonably foreseeable misuse		P
5.3	Venting		P
	Battery cases and cells incorporate a pressure relief mechanism or are constructed so that they relieve excessive internal pressure at a value and rate that will preclude rupture, explosion and self-ignition	Venting mechanism exists on the top of cylindrical cell	P
	Encapsulation used to support cells within an outer casing does not cause the battery to overheat during normal operation nor inhibit pressure relief		N/A
5.4	Temperature/voltage/current management	Cell only.	N/A
	Batteries are designed such that abnormal temperature rise conditions are prevented		N/A
	Batteries are designed to be within temperature, voltage and current limits specified by the cell manufacturer		N/A
	Batteries are provided with specifications and charging instructions for equipment manufacturers so that associated chargers are designed to maintain charging within the temperature, voltage and current limits specified		N/A
5.5	Terminal contacts		P
	Terminals have a clear polarity marking on the external surface of the battery	“+” and “-” polarity was marked on the surface of the cell, see page 4.	P
	The size and shape of the terminal contacts ensure that they can carry the maximum anticipated current		P

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
	External terminal contact surfaces are formed from conductive materials with good mechanical strength and corrosion resistance		P
	Terminal contacts are arranged to minimize the risk of short circuits		P
5.6	Assembly of cells into batteries	Cell only.	N/A
5.6.1	If there is more than one battery housed in a single battery case, cells used in the assembly of each battery have closely matched capacities, be of the same design, be of the same chemistry and be from the same manufacturer		N/A
	Each battery has an independent control and protection		N/A
	Manufacturers of cells make recommendations about current, voltage and temperature limits so that the battery manufacturer/designer may ensure proper design and assembly		N/A
	Batteries that are designed for the selective discharge of a portion of their series connected cells incorporate separate circuitry to prevent the cell reversal caused by uneven discharges		N/A
	Protective circuit components are added as appropriate and consideration given to the end-device application		N/A
	When testing a battery, the manufacturer of the battery provides a test report confirming the compliance according to this standard		N/A
5.6.2	Design recommendation for lithium systems only		N/A
	For the battery consisting of a single cell or a single cellblock: - Charging voltage of the cell does not exceed the upper limit of the charging voltage specified in Clause 8.1.2, Table 4; or		N/A
	- Charging voltage of the cell does not exceed the different upper limit of the charging voltage determined through Clause 8.1.2, NOTE 1.		N/A
	For the battery consisting of series-connected plural single cells or series-connected plural cellblocks: - The voltages of any one of the single cells or single cellblocks does not exceed the upper limit of the charging voltage, specified in Clause 8.1.2, Table 4, by monitoring the voltage of every single cell or the single cellblocks; or		N/A

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
	- The voltages of any one of the single cells or single cellblocks does not exceed the different upper limit of the charging voltage, determined through Clause 8.1.2, NOTE 1, by monitoring the voltage of every single cell or the single cellblocks		N/A
	For the battery consisting of series-connected plural single cells or series-connected plural cellblocks: - Charging is stopped when the upper limit of the charging voltage, specified in Clause 8.1.2, Table 4, is exceeded for any one of the single cells or single cellblocks by measuring the voltage of every single cell or the single cellblocks; or		N/A
	- Charging is stopped when the upper limit of the different charging voltage, determined through Clause 8.1.2, NOTE 1, is exceeded for any one of the single cells or single cellblocks by measuring the voltage of every single cell or the single cellblocks		N/A
5.7	Quality plan		P
	The manufacturer prepares and implements a quality plan that defines procedures for the inspection of materials, components, cells and batteries and which covers the whole process of producing each type of cell or battery	Complied. ISO 9001: 2015 certificate provided.	P
6	Type test conditions		P
	Tests were made with the number of cells or batteries specified in Table 1 for nickel-cadmium and nickel-metal hydride systems and Table 2 for lithium systems, using cells or batteries that are not more than six months old	Complied. Table 2 for Lithium system.	P
	Unless noted otherwise in the test methods, testing was conducted in an ambient of 20°C ± 5°C.	Tests are carried out at 20°C ± 5°C.	P
7	Specific requirements and tests (nickel systems)		N/A
7.1	Charging procedure for test purposes	Lithium system.	N/A
7.2	Intended use		N/A
7.2.1	Continuous low-rate charging (cells)		N/A
	Results: No fire. No explosion		N/A
7.2.2	Vibration		N/A
	Results: No fire. No explosion. No leakage		N/A
7.2.3	Moulded case stress at high ambient temperature		N/A
	Oven temperature (°C)..... :		—
	Results: No physical distortion of the battery casing resulting in exposure if internal components		N/A

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
7.2.4	Temperature cycling		N/A
	Results: No fire. No explosion. No leakage.		N/A
7.3	Reasonably foreseeable misuse		N/A
7.3.1	Incorrect installation cell		N/A
	The test was carried out using: - Four fully charged cells of the same brand, type, size and age connected in series, with one of them reversed; or		N/A
	- A stabilized dc power supply.		N/A
	Results: No fire. No explosion..... :		N/A
7.3.2	External short circuit		N/A
	The cells or batteries were tested until one of the following occurred: - 24 hours elapsed; or		N/A
	- The case temperature declined by 20% of the maximum temperature rise		N/A
	Results: No fire. No explosion..... :		N/A
7.3.3	Free fall		N/A
	Results: No fire. No explosion.		N/A
7.3.4	Mechanical shock (crash hazard)		N/A
	Results: No fire. No explosion. No leakage.		N/A
7.3.5	Thermal abuse		N/A
	Oven temperature (°C)..... :		—
	Results: No fire. No explosion.		N/A
7.3.6	Crushing of cells		N/A
	The crushing force was released upon: - The maximum force of 13 kN ± 1 kN has been applied; or		N/A
	- An abrupt voltage drop of one-third of the original voltage has been obtained		N/A
	The cell is prismatic type and a second set of samples was tested, rotated 90° around longitudinal axis compared to the first set		N/A
	Results: No fire. No explosion..... :		N/A
7.3.7	Low pressure		N/A
	Chamber pressure (kPa)..... :		—
	Results: No fire. No explosion. No leakage.		N/A
7.3.8	Overcharge		N/A
	Results: No fire. No explosion..... :		N/A

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
7.3.9	Forced discharge		N/A
	Results: No fire. No explosion..... :		N/A
8	Specific requirements and tests (lithium systems)		P
8.1	Charging procedures for test purposes		P
8.1.1	First procedure: This charging procedure applied to tests other than those specified in 8.1.2		P
8.1.2	Second procedure: This charging procedure applied to the tests of 8.3.1, 8.3.2, 8.3.4, 8.3.5, and 8.3.9		P
	If a cell's specified upper and/or lower charging temperature exceeds values for the upper and/or lower limit test temperatures of Table 4, the cells were charged at the specified values plus 5 °C for the upper limit and minus 5 °C for the lower limit	Charge temperature 0-60°C declared. 65°C used for upper limit tests -5°C used for lower limit tests.	P
	A valid rationale was provided to ensure the safety of the cell (see Figure A.1)..... :		P
	For a different upper limit charging voltage (i.e. other than for lithium cobalt oxide systems at 4,25 V), the applied upper limit charging voltage and upper limit charging temperatures were adjusted accordingly		P
	A valid rationale was provided to ensure the safety of the cell (see Figure A.1)..... :		P
8.2	Intended use		P
8.2.1	Continuous charging at constant voltage (cells)	Tested complied.	P
	Results: No fire. No explosion..... :	(See Table 8.2.1)	P
8.2.2	Moulded case stress at high ambient temperature (battery)	Cell only.	N/A
	Oven temperature (°C)..... :		—
	Results: No physical distortion of the battery casing resulting in exposure if internal components		N/A
8.3	Reasonably foreseeable misuse		P
8.3.1	External short circuit (cell)	Tested complied.	P
	The cells were tested until one of the following occurred: - 24 hours elapsed; or		N/A
	- The case temperature declined by 20% of the maximum temperature rise		P
	Results: No fire. No explosion..... :	(See Table 8.3.1)	P
8.3.2	External short circuit (battery)	Cell only.	N/A

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
	The cells were tested until one of the following occurred: - 24 hours elapsed; or		N/A
	- The case temperature declined by 20% of the maximum temperature rise		N/A
	In case of rapid decline in short circuit current, the battery pack remained on test for an additional one hour after the current reached a low end steady state condition		N/A
	Results: No fire. No explosion..... :	(See Table 8.3.2)	N/A
8.3.3	Free fall	Tested complied.	P
	Results: No fire. No explosion.	No fire. No explosion.	P
8.3.4	Thermal abuse (cells)	Tested complied.	P
	The cells were held at 130°C ± 2°C for: - 10 minutes; or		P
	- 30 minutes for large cells (gross mass of more than 500 g as defined in IEC 62281)		N/A
	Oven temperature (°C)..... :	130°C	—
	Gross mass of cell (g) :	<500g, small cell.	—
	Results: No fire. No explosion.	No fire. No explosion.	P
8.3.5	Crush (cells)	Tested complied.	P
	The crushing force was released upon: - The maximum force of 13 kN ± 1 kN has been applied; or		P
	- An abrupt voltage drop of one-third of the original voltage has been obtained; or		N/A
	- 10% of deformation has occurred compared to the initial dimension		N/A
	Results: No fire. No explosion..... :	(See Table 8.3.5)	P
8.3.6	Over-charging of battery	Cell only.	N/A
	Test was continued until the temperature of the outer casing: - Reached steady state conditions (less than 10°C change in 30-minute period); or		N/A
	- Returned to ambient		N/A
	Results: No fire. No explosion..... :		N/A
8.3.7	Forced discharge (cells)	Tested complied.	P
	Results: No fire. No explosion..... :	(See Table 8.3.7)	P
8.3.8	Transport tests		P

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
	Manufacturer's documentation provided to show compliance with UN Recommendations on Transport of Dangerous Goods	UN38.3 tested report provided	P
8.3.9	Design evaluation – Forced internal short circuit (cells)	Tested complied.	P
	The cells complied with national requirement for :	France, Japan, Switzerland and Republic of Korea	—
	The pressing was stopped upon: - A voltage drop of 50 mV has been detected; or		N/A
	- The pressing force of 800 N (cylindrical cells) or 400 N (prismatic cells) has been reached	800N	P
	Results: No fire	(See Table 8.3.9)	P
9	Information for safety		P
	The manufacturer of secondary cells ensures that information is provided about current, voltage and temperature limits of their products.	Information of safety mentioned in manufacturer's specification.	P
	The manufacturer of batteries ensures that equipment manufacturers and, in the case of direct sales, end-users are provided with information to minimize and mitigate hazards.		N/A
	Systems analyses performed by device manufacturers to ensure that a particular battery design prevents hazards from occurring during use of a product		N/A
	As appropriate, information relating to hazard avoidance resulting from a system analysis is provided to the end user		N/A
10	Marking		P
10.1	Cell marking		P
	Cells marked as specified in the applicable cell standards: IEC 61951-1, IEC 61951-2 or IEC 61960.	The cell is marked in accordance with IEC 61960, also see page 4.	P
10.2	Battery marking	Cell only.	N/A
	Batteries marked in accordance with the requirements for the cells from which they are assembled.		N/A
	Batteries marked with an appropriate caution statement.		N/A
10.3	Other information		P
	Storage and disposal instructions marked on or supplied with the battery.	Information for storage and disposal instructions mentioned in manufacturer's specifications.	P

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
	Recommended charging instructions marked on or supplied with the battery.	Information for recommended charging instructions mentioned in manufacturer's specifications.	P

11	Packaging		P
	The materials and packaging design are chosen so as to prevent the development of unintentional electrical conduction, corrosion of the terminals and ingress of environmental contaminants.		P

Annex A	Charging range of secondary lithium ion cells for safe use		P
A.1	General		P
A.2	Safety of lithium-ion secondary battery	Complied.	P
A.3	Consideration on charging voltage	Complied.	P
A.3.1	General		P
A.3.2	Upper limit charging voltage	3.65V, Lithium iron phosphate systems.	P
A.3.2.1	General		P
A.3.2.2	Explanation of safety viewpoint		P
A.3.2.3	Safety requirements, when different upper limit charging voltage is applied	3.65V applied.	P
A.4	Consideration of temperature and charging current		P
A.4.1	General		P
A.4.2	Recommended temperature range	See A.4.2.2.	P
A.4.2.1	General		P
A.4.2.2	Safety consideration when a different recommended temperature range is applied	Charging temperature declared by client is 0-60°C	P
A.4.3	High temperature range	Charging high temperature declared by client is 60°C	P
A.4.3.1	General		P
A.4.3.2	Explanation of safety viewpoint		P
A.4.3.3	Safety considerations when specifying charging conditions in high temperature range		P
A.4.3.4	Safety consideration when specifying new upper limit in high temperature range	65°C applied.	P
A.4.4	Low temperature range	Charging low temperature declared by client is 0°C	P
A.4.4.1	General		P
A.4.4.2	Explanation of safety viewpoint		P

IEC 62133			
Clause	Requirement + Test	Result - Remark	Verdict
A.4.4.3	Safety considerations, when specifying charging conditions in low temperature range		P
A.4.4.4	Safety considerations when specifying a new lower limit in the low temperature range	-5°C applied.	P
A.4.5	Scope of the application of charging current		P
A.5	Sample preparation		P
A.5.1	General		P
A.5.2	Insertion procedure for nickel particle to generate internal short		P
	The insertion procedure carried out at 20°C±5°C and under -25 °C of dew point		P
A.5.3	Disassembly of charged cell		P
A.5.4	Shape of nickel particle		P
A.5.5	Insertion of nickel particle to cylindrical cell		P
A.5.5.1	Insertion of nickel particle to winding core		P
A.5.5.2	Mark the position of nickel particle on the both end of winding core of the separator		P
A.5.6	Insertion of nickel particle to prismatic cell		N/A

TABLE: Critical components information					P
Object/part no.	Manufacturer/ trademark	Type/model	Technical data	Standard	Mark(s) of conformity ¹⁾
Cell	Dongguan FBTech New Energy Co.,Ltd.	32700 6000mAh	3.2V, 6000mAh, 19.2Wh	IEC 62133: 2012	Tested with appliance
-Positive electrode	CHONGQING TERUI BATTERY MATERIALS JOINT-STOCK CO, LTD	XC-555	LiFePO ₄ , Specific surface area: 11±2.0m ² /g, Tap solid density: 2.1g/cm ³ , Particle size D50: 2.5±1.0µm	--	--
-Negative electrode	Shenzhen Sinuo Industrial Development Limited Co.,LTD	MAG-09	Graphite, Particle size D50: 10-18µm, Tap solid density: 1.0-1.4g/cm ³ , Specific surface area: 1.5-3.0m ² /g	--	--
-Electrolyte	Guangzhou Tinci Materials Technology Co., Ltd	TC-E0M01	LiPF ₆ +EMC+EC+DMC Electric conductivity: 10.7~11.7mS/cm	--	--
-Separator	HuNan Chinaly New Materials Co., LTD	SHS-16µm	PE, Thickness: 16±1µm, Shutdown Temperature: 130±5°C	--	--
-Steel can	Wuxi Xinsheng Power Materials Co. Ltd	32700	Material: Ni-plated steel Thickness: Outer Wall Mouth: 4.5-7.0µm ; Outer Wall bottom ≥2.5µm; Height: 72.8mm, Diameter: 32.2mm	--	--
Supplementary information:					
¹⁾ Provided evidence ensures the agreed level of compliance. See OD-CB2039.					

7.2.1	TABLE: Continuous low rate charge (cells)					N/A
Model	Recommended charging method, (CC, CV, or CC/CV)	Recommended charging voltage V_c , (Vdc)	Recommended charging current I_{rec} , (A)	OCV at start of test, (Vdc)	Results	
Supplementary information: - No fire or explosion - No leakage - Leakage - Fire - Explosion - Bulge - Others (please explain)						

7.2.2	TABLE: Vibration		N/A
Model	OCV at start of test, (Vdc)	Results	
Supplementary information: - No fire or explosion - No leakage - Leakage - Fire - Explosion - Bulge - Others (please explain)			

7.3.1	TABLE: Incorrect installation (cells)			N/A
Model	OCV of reversed cell, (Vdc)		Results	
Supplementary information: - No fire or explosion - No leakage - Leakage - Fire - Explosion - Bulge - Others (please explain)				

7.3.2	TABLE: External short circuit					N/A
Model	Ambient (at 20°C ± 5°C or 55°C ± 5°C)	OCV at start of test, (Vdc)	Resistance of circuit, (Ω)	Maximum case temperature rise ΔT, (°C)	Results	
Supplementary information: - No fire or explosion - No leakage - Leakage - Fire - Explosion - Bulge - Others (please explain)						

7.3.6	TABLE: Crush			N/A
Model	OCV at start of test, (Vdc)	OCV at removal of crushing force, (Vdc)	Results	
Supplementary information: <ul style="list-style-type: none"> - No fire or explosion - No leakage - Leakage - Fire - Explosion - Bulge - Others (please explain) 				

7.3.8	TABLE: Overcharge			N/A
Model	OCV prior to charging, (Vdc)	Maximum charge current, (A)	Time for charging, (hours)	Results
Supplementary information: <ul style="list-style-type: none"> - No fire or explosion - No leakage - Leakage - Fire - Explosion - Bulge - Others (please explain) 				

7.3.9	TABLE: Forced discharge (cells)				N/A
Model	OCV before application of reverse charge, (Vdc)	Measured reverse charge I_r , (A)	Time for reversed charge, (minutes)	Results	
<p>Supplementary information:</p> <ul style="list-style-type: none"> - No fire or explosion - No leakage - Leakage - Fire - Explosion - Bulge - Others (please explain) 					

8.2.1	TABLE: Continuous charging at constant voltage (cells)				P
Model	Recommended charging voltage V_c , (Vdc)	Recommended charging current I_{rec} , (A)	OCV at start of test, (Vdc)	Results	
Cell #1	3.65	3.0	3.33	P	
Cell #2	3.65	3.0	3.33	P	
Cell #3	3.65	3.0	3.33	P	
Cell #4	3.65	3.0	3.33	P	
Cell #5	3.65	3.0	3.33	P	
Supplementary information:					
- No fire or explosion					
- No leakage					

8.3.1	TABLE: External short circuit (cell)					P
Model	Ambient, (°C)	OCV at start of test, (Vdc)	Resistance of circuit, (mΩ)	Maximum case temperature rise ΔT , (°C)	Results	
Samples charged at charging temperature upper limit (65°C)						
Cell #6	24.6	3.48	80.2	82.1	P	
Cell #7	24.6	3.45	81.1	81.6	P	
Cell #8	24.6	3.48	82.3	82.0	P	
Cell #9	24.6	3.49	81.6	84.3	P	
Cell #10	22.4	3.47	80.7	79.9	P	
Samples charged at charging temperature lower limit (-5°C)						
Cell #11	24.4	3.33	81.7	82.3	P	
Cell #12	24.4	3.33	82.5	80.7	P	
Cell #13	24.4	3.33	80.6	89.0	P	
Cell #14	24.4	3.33	82.1	83.1	P	
Cell #15	24.4	3.33	81.2	82.3	P	
Supplementary information:						
- No fire or explosion						

8.3.2	TABLE: External short circuit (battery)					N/A
Model	Ambient, (°C)	OCV at start of test, (Vdc)	Resistance of circuit, (Ω)	Maximum case temperature rise ΔT , (°C)	Results	
Samples charged at charging temperature upper limit						
Samples charged at charging temperature lower limit						
Supplementary information:						
- No fire or explosion						

8.3.5	TABLE: Crush					P
Model	OCV at start of test, (Vdc)	OCV at removal of crushing force, (Vdc)	Width/ diameter of cell before crush, (mm)	Required deformation for crush, (mm)	Results	
Samples charged at charging temperature upper limit (65°C)						
Cell #29	3.45	3.02	--	--	P	
Cell #30	3.44	2.12	--	--	P	
Cell #31	3.45	2.02	--	--	P	
Cell #32	3.43	1.18	--	--	P	
Cell #33	3.45	2.15	--	--	P	
Samples charged at charging temperature lower limit (-5°C)						
Cell #34	3.33	3.32	--	--	P	
Cell #35	3.33	3.31	--	--	P	
Cell #36	3.33	3.31	--	--	P	
Cell #37	3.33	3.30	--	--	P	
Cell #38	3.33	2.28	--	--	P	
Supplementary information:						
- No fire or explosion						

8.3.6		TABLE: Over-charging of battery			N/A
Constant charging current (A)					—
Supply voltage (Vdc)					—
Model	OCV before charging, (Vdc)	Resistance of circuit, (Ω)	Maximum outer casing temperature, ($^{\circ}\text{C}$)	Results	
Supplementary information:					
- No fire or explosion					

8.3.7		TABLE: Forced discharge (cells)			P
Model	OCV before application of reverse charge, (Vdc)	Measured Reverse charge I_r , (A)	Time for reversed charge, (minutes)	Results	
Cell #39	2.63	6.0	90	P	
Cell #40	2.58	6.0	90	P	
Cell #41	2.62	6.0	90	P	
Cell #42	2.58	6.0	90	P	
Cell #43	2.61	6.0	90	P	
Supplementary information:					
- No fire or explosion					

8.3.9	TABLE: Forced internal short circuit (cells)					P
Model	Chamber ambient, (°C)	OCV at start of test, (Vdc)	Particle location ¹⁾	Maximum applied pressure, (N)	Results	
Cell #1	45	3.40	1	800	P	
Cell #2	45	3.40	1	800	P	
Cell #3	45	3.39	1	800	P	
Cell #4	45	3.39	1*	800	P	
Cell #5	45	3.39	1*	800	P	
Cell #6	10	3.33	1	800	P	
Cell #7	10	3.33	1	800	P	
Cell #8	10	3.33	1	800	P	
Cell #9	10	3.33	1*	800	P	
Cell #10	10	3.33	1*	800	P	

Supplementary information:

¹⁾ Identify one of the following:

1: Nickel particle inserted between positive and negative (active material) coated area.

2: Nickel particle inserted between positive aluminium foil and negative active material coated area.

*No location 2 in this cell.

- No fire or explosion

--End of Report--